

## PRODUCT INFORMATION

Standard Grade

# KOCETAL<sup>®</sup> K300

Kocetal K300 is a general injection molding grade with a good mechanical property for wide range.

Property	Test Method	Units	Value
<b>Physical</b>			
Melt volume rate MVR 190 °C/2.16 kg	ISO 1133	cm <sup>3</sup> /10min	7.55
Specific Gravity	ISO 1183	-	1.404
Shrinkage	ISO 294-3/4	%	2.2
Water Absorption 23 °C, Equilibrium 50%RH	ISO 62	%	0.22
<b>Thermal</b>			
Melting Point	ISO 3146	°C	166
Heat Deflection Temperature under Load HDT/A 1.85 MPa ( 18.6 kg/cm <sup>2</sup> )	ISO 75-2	°C	105
Vicat Softening Temperature	ISO 306	°C	162
Flammability	UL 94	Grade	HB
<b>Mechanical</b>			
Tensile Strength 23 °C	ISO 527-1/2	MPa	62
Tensile Modulus 23 °C	ISO 527-1/2	MPa	2,580
Tensile Elongation at break 23 °C	ISO 527-1/2	%	40
Flexural Strength 23 °C	ISO 178	MPa	79
Flexural Modulus 23 °C	ISO 178	MPa	2,550
Notched Charpy Impact Strength 23 °C	ISO 179/1eA	kJ/m <sup>2</sup>	6.9
Rockwell Hardness M scale	ISO 868	M Scale	80
<b>Electrical</b>			
Surface Resistivity	IEC 60093	× 10 <sup>16</sup> Ω	1
Volume Resistivity	IEC 60093	× 10 <sup>14</sup> Ω·cm	1
Dielectric Strength	IEC 60243	kV/mm	19

The information provided in this data sheet is based on our present state of knowledge and is estimated by KOLON PLASTICS, Inc. This information should not be used as guaranteeing specification limits. KOLON PLASTICS, Inc. make no warranty and liability in connection with any use of this information.



**KOLON PLASTICS, Inc.**

KOLON TOWER, 1-23, BYULYANG-DONG, GWACHEON-CITY GYUNG GI-DO, KOREA  
Tel. 82-2-3677-3580~9 Fax. 82-2-3677-3558